

STRONG ACID CATION

HIGH-PURITY GRADE
BLACK POLYSTYRENIC GEL
8% CROSSLINKED
SODIUM FORM

ResinTech CG8-BL-HP is a high purity strong acid cation resin in sodium form. It is dark brown in color and made from a 10% cross-linked gel. The HP (high purity) designation means it is Gold Seal Certified by the WQA for use in potable water applications. CG8-BL-HP is intended for softening and other salt form applications that require potable water certification.

#### **APPLICATIONS**

- Softening Municipal
- Softening Residential

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS	
Polymer Matrix	Styrenic Gel
Ionic Form	Sodium
Fuctional Group	Sulfonic Acid
Physical Form	Spherman Beads
Particle Size	10 to 50 (S) Mesh (297-(1)90 µm)
% < 50 mesh (300μm)	LS LCALS.
Particle Size  % < 50 mesh (300µm)  Minimum Sphericity  Uniformity Coefficient  Reversible Swelling  Temp Limit  Capacity (meq/mL)	382/M
Uniformity Coefficient	1.6
Reversible Swelling	Na to H 5% to 9%
Temp Limit	280°F (138°C)
Capacity (meq/mL)	2.0
Moisture Retention	42% to 49%
Shipping Weight	51 - 53 lbs/ft³ (817 - 849 g/L)
Color	Dark Brown to Black
Regenerability	Yes

## **CERTIFICATIONS**

- WQA Gold Seal
- Kosher Certified

# C US

Revision 1.0 © 2020 ResinTech, Inc.

## **PACKAGING OPTIONS**

- 1 ft³ bags
- 1 ft<sup>3</sup> boxes
- 1 ft<sup>3</sup> drums
- 7 ft<sup>3</sup> drums
- 42 ft³ supersacks







# CG8-BL-HP

STRONG ACID CATION

# **HIGH-PURITY GRADE BLACK POLYSTYRENIC GEL 8% CROSSLINKED SODIUM FORM**





suggested on the following: 2:1 Ca:Mg ratio, 500 ppm as CaCO<sub>3</sub>, 0.2% hardness in the salt and 10% brine concentration applied co-cur through the resh over 30 minutes. No angineering downgrade has been applied.

Suggested Operating Conditions

Maximum continuous temperature Sodium form

Minimum bed denth

Backur **Backwash Expansion** 100 40°F 80 Percent of Expansion 60°F 80°F 100°F 60 40 20 n 0.0 3.0 gpm / sq.ft.

Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO<sub>3</sub>, 0.2% hardness in the salt and 10% brine concentration applied co-currently

280°F 24 inches 25 to 50 percent 25 psi 0 to 14 SU

Regenerant Concentration

Service flow rate

5 to 10 percent HCI Hydrogen cycle 1 to 8 percent H<sub>2</sub>SO<sub>4</sub> Hydrogen cycle 10 to 15 percent NaCl Salt cycle Regenerant level 4 to 15 lbs./cu.ft. 0.5 to 1.5 gpm/cu.ft. Regenerant flow rate >20 minutes Regenerant contact time Same as dilution water Displacement flow rate 10 to 15 gallons/cu.ft. Displacement volume

Same as service flow Rinse flow rate 35 to 60 gallons/cu.ft. Rinse volume 1 to 10 gpm/cu.ft.

# **IRON REMOVAL**

CG8-BL-HP has good capacity for ferrous iron. Iron content in the feedwater should not be more than 1 mg/L Fe per each 17 mg/L of hardness.

#### **AMMONIA REMOVAL**

CG8-BL-HP is slightly selective for ammonia compared to sodium but hardness is much more preferred. Ammonia is not ionized at pH above 9 and is not well removed when the pH is significantly alkaline.

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums

For operation outside these guidelines, contact ResinTech Technical Support

Revision 1.0 © 2020 ResinTech. Inc.

