PRODUCT SPECIFICATION SHEET



FINE MESH POLYSTYRENIC GEL 8% CROSSLINKED SODIUM FORM

ResinTech CG8-F is an amber-colored fine mesh strong acid cation resin in sodium form made with an 8% cross-linked gel. It offers faster kinetics and improved regeneration efficiency compared to similar resins with larger beads. CG8-F is intended for industrial softening applications that have high levels of iron in the feedwater, where resin bed depth is less than ideal, and for applications that challenge the kinetic limits of larger size resins.

APPLICATIONS

- Softening Industrial
- Demineralization
- Iron Removal

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS	
Polymer Matrix	Styrenic Gel
Ionic Form	Sodium
Fuctional Group	Sulfonte Acid
Physical Form	Spherical Bads CON
Particle Size	3500,50 US Mash (297 - 595 μm)
% < 50 mesh (300µm)	LEO/8/
Physical Form Particle Size % < 50 mesh (300µm) Minimum Sphericity Uniformity Coefficient Reversible Swelling Temp Limit	93%
Uniformity Coefficient	1.4
Reversible Swelling	Na to H 5% to 9%
Temp Limit	280°F (138°C)
Capacity (meq/mL)	2.0
Moisture Retention	42% to 52%
Shipping Weight	49 - 51 lbs/ft³ (785 - 817 g/L)
Color	Amber
Regenerability	Yes

CERTIFICATIONS

- Kosher Certified
- Halal Certified

PACKAGING OPTIONS


- 500 ml samples
- 1 ft³ bags
- 1 ft³ boxes
- 1 ft³ drums
- 7 ft³ drums
- 42 ft³ supersacks






Revision 1.0 © 2020 ResinTech, Inc. CG8-F STRONG ACID CATION

FINE MESH POLYSTYRENIC GEL 8% CROSSLINKED SODIUM FORM





Jail Dose, lbs per cu. ft.


Ja **Backwash Expansion** 100 40°F 80 Percent of Expansion 60°F 80°F 100°F 60 40 0 0.0 3.0 gpm / sq.ft.

Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO_3 , 0.2% hardness in the salt and 10% brine concentration applied co-currently

280°F 24 inches 25 to 50 percent 25 psi 0 to 14 SU

Regenerant Concentration

5 to 10 percent HCI Hydrogen cycle 1 to 8 percent H₂SO₄ Hydrogen cycle 10 to 15 percent NaCl Salt cycle Regenerant level 4 to 15 lbs./cu.ft. 0.5 to 1.5 gpm/cu.ft. Regenerant flow rate >20 minutes Regenerant contact time Same as dilution water Displacement flow rate 10 to 15 gallons/cu.ft. Displacement volume Same as service flow Rinse flow rate 35 to 60 gallons/cu.ft. Rinse volume Service flow rate 1 to 10 gpm/cu.ft.



Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums

For operation outside these guidelines, contact ResinTech Technical Support



