

# HIGH-PURITY MIXED BED POLYSTYRENIC GEL H / OH FORM

ResinTech MBD-10 is a 2:3 volumetric mixture of CG8-H-BL (dark-colored hydrogen form cation resin) and SBG1-OH (a hydroxide form type 1 strong base anion resin). The volume ratio is close to 1:1 on an equivalent basis and the component resins are chosen to separate easily for regeneration. MBD-10 is intended for use in all mixed bed deionization applications that require high resistivity and high throughput capacity.

### **APPLICATIONS**

- Cartridge Applications
- Portable Exchange Deionization (PEDI)
- High Temperature Applications
- In Place Regeneration

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS		
Polymer Matrix	Styrenic Gel	
Ionic Form	Hydrogen & Hydroxide	
Fuctional Group	Sulfonie Acid / Trimethylamine	
Physical Form	spherical Beads CON	
Particle Size	16-10°50 μS Meen (297 - 1190 μm)	
% < 50 mesh (300μm) DIS	Eallie	
Reversible Swelling	H/OH to Na/Cl -15% to -17%	
Temp Limit Moisture Retention	160°F (71°C)	
Moisture Retention	53% to 62%	
Shipping Weight	42 - 44 lbs/ft³ (673 - 705 g/L)	
Color	Amber & Amber	
Regenerability	Yes	

## **PACKAGING OPTIONS**


- 1 ft<sup>3</sup> bags
- 1 ft<sup>3</sup> boxes
- 1 ft<sup>3</sup> drums
- 7 ft<sup>3</sup> drums
- 42 ft<sup>3</sup> supersacks




Revision 1.0 © 2020 ResinTech, Inc.



# **HIGH-PURITY MIXED BED POLYSTYRENIC GEL H / OH FORM**





## **PORTABLE EXCHANGE DEIONIZATION (PEDI)**

ResinTech MBD-10 can be used in PEDI applications to remove bulk TDS from raw waters or to remove trace levels of TDS following reverse osmosis or other desalination processes. MBD-10 can be separated into its components, CG8-H-BL and SBG1-OH, for regeneration, and reused hundreds or thousands of times. The cation component, CG8-H-BL, is black in color and provides optimized color difference from SBG1-OH. This color difference is very helpful to verify resin separation during backwash.

THROUGHPUT CAPACITY (Gal/cu. ft.)			
TDS (ppm as CaO <sub>3</sub> ) Conductivity (uS/cm)	No CO <sub>2</sub> or SiO <sub>2</sub>	5 ppm $CO_2$ or SiO <sub>2</sub>	10 ppm CO <sub>2</sub> or SiO <sub>2</sub>
2/5	111,834	31,953	18,639
5/12.5	44,734	22,367	14,911
10/25	22,367	14,911	11,183
20/50	11,183	8,947	7,456
50/125	4,473	4,067	3,728
100/250	2,237	2,130	2,033
200/500	1,118	1,091	1,065
500/1250	447	443	439
1,000/2500	224	223	221

sed on NaCl (2.5uS/cm/ppm as CaCO<sub>3</sub>).

single use cartridge applications where the longest possible throughput capacity is desired.

#### SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature	140°F
Maximum intermittent temperature	180°F
Minimum bed depth	24 inches
Backwash expansion	50 to 100 percent
Maximum pressure loss	25 psi
Operating pH range	2 to 12 SU
Service flow rate	
Working	1 to 5 gpm per cu. ft.
Polishing	3 to 15 gpm per cu. ft.

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support



Revision 1.0 © 2020 ResinTech, Inc.