PRODUCT SPECIFICATION SHEET

MBD-15-SC

MIXED BED

SEMICONDUCTOR GRADE MIXED BED
HIGH PURITY & HIGH CAPACITY
POLYSTYRENIC GEL
H / OH FORM

ResinTech MBD-15-SC is a 2:3 volumetric mixture of CG8-H-BL (a dark-colored hydrogen form cation resin) and SBG1P-OH (a hydroxide form type 1 porous strong base anion resin). The SC grade means it has been functionally tested to produce > 18 megohm resistivity and under 50 ppb of TOC. MBD-15-SC is intended for use in all mixed bed deionization applications that require high resistivity and high throughput capacity.

APPLICATIONS

• Portable Exchange Deionization (PEDI)

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS			
Polymer Matrix	Styrenic Gel		
Ionic Form	Hydrogen & Hydroxide		
Fuctional Group	Sulfonie Acid / Trimethylamine		
Physical Form	Spherical Boards CON		
Particle Size	1670 50 US Mesh (297 - 1190 µm)		
Particle Size % < 50 mesh (300μm)	EMIC		
% < 50 mesh (300μm) Reversible Swelling Temp Limit Capacity (meq/mL) Moisture Retention	H/OH to Na/Cl -15% to -17%		
Temp Limit	140°F (60°C)		
Capacity (meq/mL)	0.55		
Moisture Retention	57% to 65%		
Shipping Weight	42 - 44 lbs/ft³ (673 - 705 g/L)		
Color	Brown / Black & Amber		
Regenerability	Yes		

PACKAGING OPTIONS

- 500 ml samples
- 1 ft³ bags
- 1 ft³ boxes
- 1 ft³ drums
- 7 ft³ drums
- 42 ft³ supersacks






Revision 1.0 © 2020 ResinTech, Inc.

MBD-15-SC

MIXED BED

SEMICONDUCTOR GRADE MIXED BED **HIGH PURITY & HIGH CAPACITY POLYSTYRENIC GEL** H / OH FORM



		Backwash Expansion				
1	100					
<u>_</u>	80	— 40°F — 60°F				B
ansic	60				NSTK	-11
Percent of Expansion	40				CHE	, ,,
				ACH	PAC	X
Δ.	20		A	NWN	1.1	
	0 0.	0 1.	0 2.	.0	3.0	4.0
			gpm /	sq.ft.		

4	00 -		•		
	80	40°F			
Percent of Expansion	60			nis	PH-
nt of Ex	40			CY	IEN,
Percel	20		APAC	IN AP	VO.
	0.0	0 1.0	2.0	3.0	4.0
			gpm / sq.ft.		

PORTABLE EXCHANGE DEIONIZATION (PEDI)

ResinTech MBD-15-SC can be used in PEDI applications to remove bulk TDS from raw waters or to remove trace levels of TDS following reverse osmosis or other desalination processes. The mixed resin can be separated into its components, CG8-H-BL and SBG1P-OH, for regeneration, and reused hundreds or thousands of times. The cation component, CG8-H-BL, is dark in color and provides optimized color difference from SBG1P-OH. This color difference can verify resin separation during backwash.

THR	THROUGHPUT CAPACITY (Gal/cu. ft.)				
TDS (ppm as CaO ₃) Conductivity (uS/cm)	No CO ₂ or SiO ₂	5 ppm CO ₂ or SiO ₂	10 ppm CO ₂ or SiO ₂		
2/5	102,515	29,290	17,086		
5/12.5	41,006	20,503	13,669		
10/25	20,503	13,669	10,251		
20/50	10,251	8,201	6,834		
50/125	4,101	3,728	3,417		
100/250	2,050	1,953	1,864		
200/500	1,025	1,000	976		
500/1250	410	406	402		
1,000/2500	205	204	203		

to TDS. Capacity is based on the anion pronent and is for virgin esin, reliewing the initital exhaustion and regeneration sub-pert cycles will likely be shorter, depending on how skillfully the resins are separated,

IN PLACE REGENERATION

ResinTech MBD-15-SC is ideal for in place regenerated mixed beds, especially if they are set up for the 60/40 anion to cation ratio that is optimum for most mixed bed polishers.

SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature 140°F Minimum bed depth 24 inches Backwash expansion 50 to 100 percent Maximum pressure loss 25 psi 2 to 12 SU Operating pH range Service flow rate

Working

1 to 5 gpm per cu. ft. Polishing 3 to 15 gpm per cu. ft.

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support



