# **PRODUCT SPECIFICATION SHEET**



HIGH-PURITY MIXED BED
POLYSTYRENIC GEL
H / OH FORM

ResinTech MBD-15 is a 2:3 volumetric mixture of CG8-H-BL (a dark-colored hydrogen form cation resin) and SBG1P-OH (a hydroxide form type 1 porous strong base anion resin). The volume ratio is close to 1:1 on an equivalent basis and the component resins are chosen to separate easily for regeneration. MBD-15 is intended for use in all mixed bed deionization applications that require high resistivity and high throughput capacity.

### **APPLICATIONS**

- Portable Exchange Deionization (PEDI)
- In-Place Regeneration

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS				
Polymer Matrix	Styrenic Gel			
Ionic Form	Hydrogen & Hydroxide			
Fuctional Group	Sulfone Acid / Trimethylamine			
Physical Form	Spherical Bads CON			
Particle Size	16 to 50 US Mash (297 - 1190 µm)			
% < 50 mesh (300μm)	FEAMO			
% < 50 mesh (300μm)  Reversible Swelling  Temp Limit  Capacity (meq/mL)  Moisture Retention	H/OH to Na/Cl -15% to -17%			
Temp Limit	140°F (60°C)			
Capacity (meq/mL)	0.55			
Moisture Retention	57% to 65%			
Shipping Weight	42 - 44 lbs/ft³ (673 - 705 g/L)			
Color	Brown / Black & Amber			
Regenerability	Yes			

#### **PACKAGING OPTIONS**

- 500 ml samples
- 1 ft³ bags
- 1 ft³ boxes
- 1 ft<sup>3</sup> drums
- 7 ft<sup>3</sup> drums
- 42 ft<sup>3</sup> supersacks







**MBD-15** 

MIXED BED

# **HIGH-PURITY MIXED BED POLYSTYRENIC GEL** H / OH FORM





	Buokwaon Expansion						
100							
00	— 40°F — 60°F				21B		
xpansio 99				DIST			
Percent of Expansion				CH	CY		
Per 20		N	ACLI	LAPA	,0		
0	.0 1.	0 2.	M	3.0	4.0		
gpm / sq.ft.							

### PORTABLE EXCHANGE DEIONIZATION (PEDI)

ResinTech MBD-15 can be used in PEDI applications to remove bulk TDS from raw waters or to remove trace levels of TDS following reverse osmosis or other desalination processes. The mixed resin can be separated into its components, CG8-H-BL and SBG1P-OH, for regeneration, and reused hundreds or thousands of times. The cation component, CG8-H-BL, is dark in color and provides optimized color difference from SBG1P-OH. This color difference is very helpful to verify resin separation during backwash.

THROUGHPUT CAPACITY (Gal/cu. ft.)						
TDS (ppm as CaO <sub>3</sub> ) Conductivity (uS/cm)	No CO <sub>2</sub> or SiO <sub>2</sub>	5 ppm CO <sub>2</sub> or SiO <sub>2</sub>	10 ppm CO <sub>2</sub> or SiO <sub>2</sub>			
2/5	102,515	29,290	17,086			
5/12.5	41,006	20,503	13,669			
10/25	20,503	13,669	10,251			
20/50	10,251	8,201	6,834			
50/125	4,101	3,728	3,417			
100/250	2,050	1,953	1,864			
200/500	1,025	1,000	976			
500/1250	410	406	402			
1,000/2500	205	204	203			

ns to TDS. Capacity is based on the anion component and is for virgin resin. Pellowing the initital exhaustion and regeneration sub-sequent cycles will likely be shorter, depending on how skillfully the resins are separated,

## IN PLACE REGENERATION

ResinTech MBD-15 is ideal for in place regenerated mixed beds, especially if they are set up for the 60/40 anion to cation ratio that is optimum for most mixed bed polishers.

### SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature 140°F Minimum bed depth 24 inches Backwash expansion 50 to 100 percent Maximum pressure loss 25 psi 2 to 12 SU Operating pH range Service flow rate Working 1 to 5 gpm per cu. ft.

Polishing 3 to 15 gpm per cu. ft.

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support

© 2020 ResinTech, Inc.

