# **PRODUCT SPECIFICATION SHEET**

**MBD-16** 

MIXED BED

HIGH-PURITY MIXED BED

10% CROSSLINKED CATION

POLYSTYRENIC GEL

H / OH FORM

ResinTech MBD-16 is a 2:3 volumetric mixture of CG10-H-BL (a dark-colored hydrogen form cation resin) and SBG1P-OH (a hydroxide form type 1 porous strong base anion resin). The volume ratio is close to 1:1 on an equivalent basis and the component resins are chosen to separate easily for regeneration. MBD-16 is intended for use in all mixed bed deionization applications that require high resistivity and high throughput capacity.

### **APPLICATIONS**

• Portable Exchange Deionization (PEDI)

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS		
Polymer Matrix	Styrenic Gel	
Ionic Form	Hydrogen & Hydroxide	
Fuctional Group	Sulfonie Acid / Trimethylamine	
Physical Form	Spherical Boards CON	
Particle Size	1670 50 US Mesh (297 - 1190 µm)	
Particle Size % < 50 mesh (300μm)	TENNO!	
% < 50 mesh (300μm)  Reversible Swelling  Temp Limit  Capacity (meq/mL)  Moisture Retention	H/OH to Na/Cl -15% to -17%	
Temp Limit	250°F (121°C)	
Capacity (meq/mL)	0.6	
Moisture Retention	56% to 64%	
Shipping Weight	42 - 44 lbs/ft³ (673 - 705 g/L)	
Color	Brown / Black & Amber	
Regenerability	Yes	

### **PACKAGING OPTIONS**

- 1 ft³ bags
- 1 ft<sup>3</sup> drums
- 1 ft³ boxes
- 7 ft<sup>3</sup> drums
- 42 ft<sup>3</sup> supersacks







Revision 1.0 © 2020 ResinTech, Inc. **MBD-16** 

MIXED BED

**HIGH-PURITY MIXED BED** 10% CROSSLINKED CATION **POLYSTYRENIC GEL** H / OH FORM





## PORTABLE EXCHANGE DEIONIZATION (PEDI)

ResinTech MBD-16 can be used in almost all PEDI applications to remove bulk TDS from raw waters or to remove trace levels of TDS following reverse osmosis or other membrane processes. The mixed resin can be separated into its components, CG10-H-BL and SBG1, for regeneration, and reused hundreds or thousands of times. The use of the more dense CG10-H-BL cation component in MBD-16 allows for more efficient resin separation compared to MBD-10 or MBD-15. This resin color difference is helpful to verify resin separation ahead of the regeneration process.

THROUGHPUT CAPACITY (Gal/cu. ft.)			
TDS (ppm as CaO <sub>3</sub> ) Conductivity (uS/cm)	No CO <sub>2</sub> or SiO <sub>2</sub>	5 ppm CO <sub>2</sub> or SiO <sub>2</sub>	10 ppm CO <sub>2</sub> or SiO <sub>2</sub>
2/5	111,834	31,953	18,639
5/12.5	44,734	22,367	14,911
10/25	22,367	14,911	11,183
20/50	11,183	8,947	7,456
50/125	4,473	4,067	3,728
100/250	2,237	2,130	2,033
200/500	1,118	1,091	1,065
500/1250	447	443	439
1,000/2500	224	223	221

140°F 180°F 24 inches 50 to 75 percent Backwash expansion Maximum pressure loss 25 psi 2 to 12 SU Operating pH range Service flow rate

Working 1 to 5 gpm per cu. ft. Polishing 3 to 15 gpm per cu. ft.

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support

Revision 1.0 © 2020 ResinTech. Inc.

