

TYPE I ANION POLYSTYRENIC MACROPOROUS CHLORIDE FORM

ResinTech SBMP1 is a chloride form type 1 macroporous strong base anion resin. It is optimized for waters that punish other anion resins. SBMP1 is intended for high flow rate and high-temperature polishing applications, and for other applications that require the highest possible physical strength and chemical durability.

APPLICATIONS

- Demineralization
- Radwaste Removal

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS	
Polymer Matrix	Styrenic Macroporous
Ionic Form	Chloride
Fuctional Group	Trimethylamine
Physical Form	Spherical Beads
Particle Size	46 to 50 US Mesh (297 - 1990 µm)
% < 50 mesh (300μm)	SoucALS.
Minimum Sphericity	25% MIC
Uniformity Coefficient	1.6
Reversible Swelling	CI to OH 15% to 20%
Temp Limit	170°F (77°C)
Capacity (meq/mL)	1.1
Moisture Retention	50% to 63%
Shipping Weight	41 - 43 lbs/ft ³ (657 - 689 g/L)
Color	White to Cream
Regenerability	Yes

CERTIFICATIONS

- WQA Gold Seal
- Halal Certified
- Kosher Certified

PACKAGING OPTIONS

- 500 ml samples
- 1 ft³ bags
- 1 ft³ boxes
- 1 ft³ drums
- 7 ft³ drums
- 42 ft³ supersacks

RESINTECHINC.

Revision 1.0 © 2020 ResinTech, Inc.





TYPE I ANION POLYSTYRENIC MACROPOROUS CHLORIDE FORM



RADWASTE

ResinTech SBMP1 is ideally suited for radwaste applications requiring the removal of radioactive anions, especially when the feed is significantly radioactive. The high crosslinking content of SBMP1 gives it improved resistance to chemical damage caused by ionizing radiation. Structural integrity is maintained up to approximately 1 x 109 rads exposure.

SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature 170°F Chloride form Minimum bed depth 24 inches **Backwash Expansion** 25 to 50 percent 20 psi 0 to 14 SU 2 to 6 percent NaOH 2 to 10 percent NaCl 4 to 10 lbs./cu.ft. 0.25 to 1.0 gpm/cu.ft. >40 minutes Same as dilution water 10 to 15 gallons/cu.ft. gpm / sq.ft. Rinse flow rate Same as service flow Rinse volume 35 to 60 gallons/cu.ft. Service flow rate 1 to 10 gpm/cu.ft.

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support

Revision 1.0 © 2020 ResinTech, Inc.

100

80

60

40

20

0

0

Percent of Expansion

40°F

60°F

80°F 100°F

1.0

