AGC-40 C

COCONUT SHELL CARBON

**PREMIUM GRADE DRY COCONUT SHELL CARBON COARSE MESH (12X40)** 

ResinTech AGC-40 C is a 12 x 40 mesh coconut shell based granular activated carbon. It has similar properties to other products in the AGC-40 family. ResinTech AGC-40 C is intended for chlorine or NOM removal where rapid adsorption is required. It is Gold Seal Certified by the WQA for use in potable water applications.

## **APPLICATIONS**

- Chlorine Reduction
- Organics Reduction

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS	
Physical Form	Carbonaceous Granules
Particle Size	12 to 40 US Mesh (400 - 1680 μm)
% < 50 mesh (300μm)	< 5% \ C.
Temp Limit	2/2°F (700°C) P ., M
Moisture Retention	<5% OCN/A \ S.O
Shipping Weight	29 - 31 Nos/ft (465 - 497 g/L)
Color	Black
Uniform Particle Size	Yes
PACKAGING OPTIONS ANWW.AP	
PACKAGING OPTIONS WWW.	SUGGESTED OPERATING CONDITIONS

## **PACKAGING OPTIONS**

• 1 ft³ bags

• 1 ft³ boxes

• 1 ft<sup>3</sup> drums

• 7 ft<sup>3</sup> drums

• 42 ft<sup>3</sup> supersacks

## **CERTIFICATIONS**

WQA Gold Seal



Revision 1.0 © 2020 ResinTech, Inc.

## SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature

250°F Sodium form

Minimum bed depth

Chlorine removal 24 inches Chloramine removal 36 inches Support bed 12 inches Backwash expansion 15 to 25 percent Backwash flow rate 6 to 10 gpm/sq.ft.

Service flow rate

Chlorine removal 1 to 5 gpm/cu.ft. 0.5 to 1.0 gpm/cu.ft. Chloramine removal

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support



