AGC-40 CA

COCONUT SHELL CARBON

PREMIUM GRADE ACID-WASHED SEMI MOIST COCONUT SHELL CARBON COARSE MESH (12X40)

ResinTech AGC-40 CA is a semi moist 12 x 40 mesh coconut shell based granular activated carbon. It is dust free and acid washed to neutralize pH and conductivity when first placed into use. ResinTech AGC-40 CA is intended for chlorine or NOM removal where rapid adsorption is required. It is Gold Seal Certified by the WQA for use in potable water applications.

APPLICATIONS

- Chlorine Reduction
- Organics Reduction

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS		
Physical Form		Carbonaceous Granules
Particle Size		12 to 40 US Mesh (400 - 1680 µm)
% < 50 mesh (300μm)		< 5% \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \
Temp Limit		212°F400°C)-P.,
Moisture Retention	aBU	20% t 30% C
Shipping Weight	SISTRING	37 - 39 (LG)/ft (593 - 625 g/L)
Color	DIENIE	- Haller
Uniform Particle Size	CHE CHE	Yes
	APACINI APA	
PACKAGING OPTIONS	APACHE CHE	SUGGESTED OPERATING CONDITIONS
• 1 ft ³ bage	• 1 ft ³ drume	Maximum continuous temporature

PACKAGING OPTIONS

- 1 ft³ bags
- 1 ft³ boxes
- 1 ft³ drums
- 7 ft³ drums
- 42 ft³ supersacks

CERTIFICATIONS

WQA Gold Seal



Revision 1.0 © 2020 ResinTech, Inc.

SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature

250°F Sodium form

Minimum bed depth

Chlorine removal 24 inches Chloramine removal 36 inches Support bed 12 inches Backwash expansion 15 to 25 percent Backwash flow rate 6 to 10 gpm/sq.ft.

Service flow rate

Chlorine removal 1 to 5 gpm/cu.ft. Chloramine removal 0.5 to 1.0 gpm/cu.ft.

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums

For operation outside these guidelines, contact ResinTech Technical Support



