## PRODUCT SPECIFICATION SHEET

# **AGC-PFx**

**COCONUT SHELL CARBON** 

**PFAS SELECTIVE ACID-WASHED SEMI MOIST COCONUT SHELL CARBON STANDARD MESH (12X40)** 

ResinTech AGC-PFx is a premium grade, semi-moist, acid-washed, coconut shell-based granular activated carbon. It has chemically enhanced pore size to facilitate the removal of Per- and Polyfluoroalkyl compounds (PFCs) such as PFOS, PFOA, and others. AGC-PFx is intended for use as a stand alone media bed or as a top layer with other medias to facilitate PFC removal. AGC-PFx is Gold Seal Certified by the WQA for use in potable water applications.

#### **APPLICATIONS**

- PFAS Reduction
- Organics Removal



TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS	
Physical Form	Carbonaceous Granules
Particle Size	12 to 40 US Mesh (400 + 1680 µm)
% < 40 mesh (400μm)	EDO DRP .; OM
Temp Limit	242°F (400°C) S.
Moisture Retention	20% to \$0%
Shipping Weight	3V - 39 lbs/ft <sup>3</sup> (593 - 625 g/L)
Color	Black
AP AUN. AP	
PACKAGING OPTIONS WITH	SUGGESTED OPERATING CONDITIONS

#### **PACKAGING OPTIONS**

- 1 ft³ bags
- 1 ft3 boxes
- 1 ft<sup>3</sup> drums
- 7 ft<sup>3</sup> drums
- 42 ft<sup>3</sup> supersacks

### **CERTIFICATIONS**

WQA Gold Seal\*

#### SUGGESTED OPERATING CONDITIONS

Maximum temperature 212°F Minimum Bed Depth

PFAS removal - Standalone

- Layered on top of

other media Support bed Backwash Expansion

Backwash Flow rate Service Flow Rate PFAS removal

> 36 inches (or 36 inch min.) > 12 inches (or 12 inch min.)

12 inches suggested

15 to 25% 6 to 10 gpm/sq.ft.

> 1 gpm/cu.ft. max (7-10 minute EBCT)

Revision 1.2 ResinTech, Inc.®



<sup>\*</sup> NSF/ANSI/CAN 61: Drinking Water System Components - Health Effects